

APPENDIX A



T410  
10-08

**West Virginia Division of Highways**  
Degree of Particle Coating of Bituminous-Aggregate Mixtures  
ASTM D2489

Lab Number:		Date Tested:	
Technician:		Cold-Mix Type:	
Cold-Mix Source:			
Cold-Mix Stockpile Location:			
Test Sample Number 1			
(A) Total Number of Particles:		(B) Number of coated particles:	
(C) Percentage of Coated Particles = $( B / A ) \times 100$ :			
Test Sample Number 2			
(D) Total Number of Particles:		(E) Number of coated particles:	
(F) Percentage of Coated Particles = $( E / D ) \times 100$ :			
Average Percent Coated Particles = $( C + F ) / 2$ :			
Pass / Fail:			
97% Coating Requirement for First Week After Stockpiling 95% Coating Requirement Up To 90 Days After Stockpiling			
Remarks:			